

Aluminum Nitride Powder



RFS Series - Product Datasheet

Thrutek Applied Materials produces over 100 standard and customized grades of AIN powders to meet a wide range of application requirements and has over 14 years of expertise in research and development of Aluminum Nitride powders.

RFS Series

Spherical AIN powder makes it possible to achieve high thermal conductivity in fillers.

RFS Series spherical aluminum nitride powders have high purity spherical shaped particles designed for excellent flowability and loading.

The larger mean particle size and spherical shape not only provides a higher filling rate but also much improved thermal conductivity.

RFS Series AIN powders are surface coated for better coupling with silicone and offer improved resistance against hydrolysis.

Key Applications

RFS Series can be used in a variety of silicone polymers to develop highly thermal conductive products such as adhesives, gels, grease, pads and tapes, etc.

Features & Benefits


- Spherical Shaped Particles
- Sharp PSD and Low impurities
- Surface coated for better bonding with silicone polymers
- Water Resistant variants available
- Customizable PSD and surface coating


Properties		Available Grades			
		AIN300RFS	AIN550RFS	AIN800RFS	AIN13tRFS
Particle Type		Sintered Agglomerated			
Particle Shape		Spherical			
Surface Coating		Surface coated for improved bonding with silicone polymers			
Particle Size	D10	25 µm	40 µm	58 µm	100 µm
	D50	30 µm	55 μm	80 µm	130 µm
	D90	38 µm	72 µm	108 µm	170 µm
Specific Surface Area (SSA)		< 0.13 m ² /g	< 0.067 m ² /g	$< 0.05 \text{ m}^2/\text{g}$	$< 0.03 \text{ m}^2/\text{g}$
Impurities	Ca	<100 ppm			
	Fe	<150 ppm			
	Si	<300 ppm			
	Pb	<10 ppm			
	С	<100 ppm			
	0	<2.5 wt%			
Anti-Hydrolysis	Treatment	No water resistance treatment applied			
	Rating	Surface-coated AIN powder hydrolyzes in water in 24 to 72 hours			
Application		Ideally used as main filler in silicone polymers			


Chemical Name Aluminum Nitride | Formula AIN | CAS Number 24304-00-5


Form Powder | Color Gray | Purity ≥ 97% | Melting Point > 2200 °C | Density 3.26 g/cm³


SEM Photo & Particle Size Distribution




















Disclaimer: Data represented in this document are typical values only and not guaranteed. Thrutek reserves the right to make changes to the product information contained herein without notice.